



**Upset Drill Pipe Tubing**

**1.660" X 3.02 lb/ft TenarisHydril CS**

# Upset Drill Pipe Tubing

## 1.660" X 3.02 lb/ft TenarisHydril CS



Specification	
OEM	TenarisHydril
Country of Origin	Romania
Nominal Tubing OD	1.660"
Drift Size	1.184"
Steel Grade	L-80
Nominal Weight	3.02 lb/ft
Nominal Wall Thickness	0.191"
Nominal ID	1.278"
Connection Length	
Connection Make Up Loss	2.22"
Manufacturing Criteria	API 5CT

Tubing Capacities		
Body Yield Strength	71,000 lbs	316 kN
API Collapse	16,290 psi	1123 bar
Internal Yield	16,110 psi	1111 bar
Joint Strength	71,000 lbs	316 kN

Connection Specifications			
Connection	1 ¼" TenarisHydril CS	Compatible With	1.660" TS-8
OD	1.927"	ID	1.218"
Connection Length		Minimum	
		Standard	1 recut
		Type 2	2 recut
		Type 3	3 recut
Minimum Make Up Torque	600 lb/ft	810 N m	
Optimum Make Up Torque	700 lb/ft	946 N m	
Maximum Make Up Torque	800 lb/ft	1081 N m	
Connection Tensile Efficiency	100%	Inspection Criteria	API 5A5, API 5CT

The information on this specification sheet is provided for illustration purposes only and is taken from information available from the manufacturer and other public sources. Saltire Energy Limited accepts no responsibility or liability for the accuracy of the information provided or for any error, omission or misstatement.

# Our Locations

## SALTIRE ENERGY HUB

Badentoy Crescent, Portlethen

Aberdeen, AB12 4YD

[enquiries@saltire-energy.com](mailto:enquiries@saltire-energy.com)

+44 (0)1224 872228

+44 (0)1224 897541

## FAR EAST

No.20 Tuas Ave 10, Singapore, 639144

[enquiries@saltire-energy.com](mailto:enquiries@saltire-energy.com)

+44 (0)1224 872228

+44 (0)1224 897541

## MIDDLE EAST

Musaffah, Abu Dhabi, 53161

[enquiries@saltire-energy.com](mailto:enquiries@saltire-energy.com)

+44 (0)1224 872228

+44 (0)1224 897541

## NORWAY

Hamrasletta 5, 4056 Tanager, Stavanger

[enquiries@saltire-energy.com](mailto:enquiries@saltire-energy.com)

+44 (0)1224 872228

+44 (0)1224 897541



[www.saltire-energy.com](http://www.saltire-energy.com)