



TenarisHydril TSHW511 Flush Joint Tubing

2.875" X 6.40 lb/ft

DRILL PIPE TUBING

2.875" X 6.40 lb/ft TenarisHydril TSHW511 Flush Joint Tubing



Specification	
OEM	TenarisHydril
Country of Origin	UK, Romania, Argentina
Nominal Tubing OD	2 7/8" (2.875")
Drift Size	2.347"
Steel Grade	P-110
Nominal Weight	6.40 lb/ft
Nominal Wall Thickness	0.217"
Nominal ID	2.441"
Connection Length	
Connection Make Up Loss	2.27"
Manufacturing Criteria	API 5CT

Tubing Capacities		
Body Yield Strength	199,000 lbs	886 kN
API Collapse	14,540 psi	1003 bar
Internal Yield	14,530 psi	1002 bar
Joint strength	109,000 lbs	

Connection Specifications			
Connection	2 7/8" TSHW511	Compatible With	
OD	2.875"	ID	2.377"
Connection Length	Minimum		
	Standard	1 recut	
	Type 2	2 recut	
	Type 3	3 recut	
Minimum Make Up Torque	700 lb/ft	946 N m	
Optimum Make Up Torque	800 lb/ft	1080 N m	
Maximum Make Up Torque	1,200 lb/ft	1622 N m	
Connection Tensile Efficiency	54.9%	Inspection Criteria	API 5A5, API 5CT

The information on this specification sheet is provided for illustration purposes only and is taken from information available from the manufacturer and other public sources. Saltire Energy Limited accepts no responsibility or liability for the accuracy of the information provided or for any error, omission or misstatement.

Our Locations

SALTIRE ENERGY HUB

Badentoy Crescent, Portlethen

Aberdeen, AB12 4YD

enquiries@saltire-energy.com

+44 (0)1224 872228

+44 (0)1224 897541

FAR EAST

No.20 Tuas Ave 10, Singapore, 639144

enquiries@saltire-energy.com

+44 (0)1224 872228

+44 (0)1224 897541

MIDDLE EAST

Musaffah, Abu Dhabi, 53161

enquiries@saltire-energy.com

+44 (0)1224 872228

+44 (0)1224 897541

NORWAY

Hamrasletta 5, 4056 Tanager, Stavanger

enquiries@saltire-energy.com

+44 (0)1224 872228

+44 (0)1224 897541



www.saltire-energy.com