



TenarisHydril TSHW511 Flush Joint Tubing

4.000" X 11.6 lb/ft

DRILL PIPE TUBING

4.000" X 11.6 lb/ft TenarisHydril TSHW511 Flush Joint Tubing



| Specification | |
|-------------------------|------------------------|
| OEM | TenarisHydril |
| Country of Origin | UK, Romania, Argentina |
| Nominal Tubing OD | 4" (4.00") |
| Drift Size | 3.303" |
| Steel Grade | P-110 |
| Nominal Weight | 11.6 lb/ft |
| Nominal Wall Thickness | 0.286" |
| Nominal ID | 3.428" |
| Connection Length | |
| Connection Make Up Loss | 2.740" |
| Manufacturing Criteria | API 5CT |

| Tubing Capacities | | |
|---------------------|-------------|--|
| Body Yield Strength | 367,000 lbs | |
| API Collapse | 13,150 psi | |
| Internal Yield | 13,760 psi | |
| Joint strength | 224,000 lbs | |

| Connection Specifications | | | |
|-------------------------------|-------------|---------------------|------------------|
| Connection | 4" TSHW511 | Compatible With | |
| OD | 4.031" | ID | 3.334" |
| Connection Length | Minimum | | |
| | Standard | 1 recut | |
| | Type 2 | 2 recut | |
| | Type 3 | 3 recut | |
| Minimum Make Up Torque | 1,700 lb/ft | 1757 N m | |
| Optimum Make Up Torque | 2,000 lb/ft | 2162 N m | |
| Maximum Make Up Torque | 3,00 lb/ft | 2838 N m | |
| Connection Tensile Efficiency | 61.0% | Inspection Criteria | API 5A5, API 5CT |

The information on this specification sheet is provided for illustration purposes only and is taken from information available from the manufacturer and other public sources. Saltire Energy Limited accepts no responsibility or liability for the accuracy of the information provided or for any error, omission or misstatement.

Our Locations

SALTIRE ENERGY HUB

Badentoy Crescent, Portlethen

Aberdeen, AB12 4YD

enquiries@saltire-energy.com

+44 (0)1224 872228

+44 (0)1224 897541

FAR EAST

No.20 Tuas Ave 10, Singapore, 639144

enquiries@saltire-energy.com

+44 (0)1224 872228

+44 (0)1224 897541

MIDDLE EAST

Musaffah, Abu Dhabi, 53161

enquiries@saltire-energy.com

+44 (0)1224 872228

+44 (0)1224 897541

NORWAY

Hamrasletta 5, 4056 Tanager, Stavanger

enquiries@saltire-energy.com

+44 (0)1224 872228

+44 (0)1224 897541



www.saltire-energy.com