




Upset Drill Pipe Tubing

4.500" X 15.5 lb/ft TenarisHydril TSHW533

Upset Drill Pipe Tubing

4.500" X 15.5 lb/ft TenarisHydril TSHW533



Specification	
OEM	TenarisHydril
Country of Origin	UK, Romania, Argentina
Nominal Tubing OD	4 ½" (4.500")
Drift Size	3.701"
Steel Grade	L-80
Nominal Weight	15.5 lb/ft
Nominal Wall Thickness	0.337"
Nominal ID	3.826"
Connection Length	
Connection Make Up Loss	4.09"
Manufacturing Criteria	API 5CT

Tubing Capacities		
Body Yield Strength	353,000 lbs	1570 kN
API Collapse	11,090 psi	764 bar
Internal Yield	10,480 psi	722 bar
Joint Strength	353,000 lbs	1570 kN

Connection Specifications			
Connection	4 ½" TSHW533	Compatible With	TSH503 TSH553 TSH563
OD	4.992"	ID	3.776"
Connection Length		Minimum	
		Standard	1 recut
		Type 2	2 recut
		Type 3	3 recut
Minimum Make Up Torque	5,800 lb/ft	7838 N m	
Optimum Make Up Torque	7,000 lb/ft	9459 N m	
Maximum Make Up Torque	10,200 lb/ft	13784 N m	
Connection Tensile Efficiency	100%	Inspection Criteria	API 5A5, API 5CT

The information on this specification sheet is provided for illustration purposes only and is taken from information available from the manufacturer and other public sources. Saltire Energy Limited accepts no responsibility or liability for the accuracy of the information provided or for any error, omission or misstatement.

Our Locations

SALTIRE ENERGY HUB

Badentoy Crescent, Portlethen

Aberdeen, AB12 4YD

enquiries@saltire-energy.com

+44 (0)1224 872228

+44 (0)1224 897541

FAR EAST

No.20 Tuas Ave 10, Singapore, 639144

enquiries@saltire-energy.com

+44 (0)1224 872228

+44 (0)1224 897541

MIDDLE EAST

Musaffah, Abu Dhabi, 53161

enquiries@saltire-energy.com

+44 (0)1224 872228

+44 (0)1224 897541

NORWAY

Hamrasletta 5, 4056 Tanager, Stavanger

enquiries@saltire-energy.com

+44 (0)1224 872228

+44 (0)1224 897541



www.saltire-energy.com