




## **SMFI Drilling Heavyweight Drill Pipe**

**6.625" X Welded HWDP Range 2**

# SMFI Heavyweight Drill Pipe

## 6.625" X Welded HWDP Range 2



Specification	
OEM	SMFI
Country of Origin	France
Nominal OD	6 5/8" (6.625")
Nominal ID	4 1/2" (4.500")
Steel Grade	AISI 1340 65 ksi min
Nominal Weight	70.00#
Nominal Wall Thickness	1.06"
Drift Size	
Hardbanding	Arncos 200XT
Hardbanding Center Wear Band	Arncos 200XT
Pin Length	27"
Box Length	21"
Average Weight Per Joint	2,178 lbs (990 kgs)
Manufacturing Criteria	API Spec 7-1 /NS-1
Pipe Body Capacities	
Yield Strength	1,210,000 lbs
API Collapse	17,500 psi
Torsional Yield Strength	140,000 lb/ft
Pipe Burst Resistance	20,800 psi

### Tool Joint / Connection Specifications

Connection	6 5/8" FH	Compatible With	
OD	8" (8.000")	ID	5" (5.000")
Type of Tool Joint	Welded		100 ksi
Adjusted Weight	71,23 lb/ft	Average Length	31.0 ft
Tensile Yield	1,210,000 lbs	Torsional Yield	61,000 ft/lbs
Recommended Make Up Torque	38,100 lb/ft	Min Make Up Torque	36,200 lb/ft
		Max Make Up Torque	40,000 lb/ft
Center Upset OD	7 1/8" (7.125)	Fluid Capacity	0.83 gal/ft
Type of Upset		Inspection Criteria	NS-2

The information on this specification sheet is provided for illustration purposes only and is taken from information available from the manufacturer and other public sources. Saltire Energy Limited accepts no responsibility or liability for the accuracy of the information provided or for any error, omission or misstatement.

# Our Locations

## **SALTIRE ENERGY HUB**

Badentoy Crescent, Portlethen

Aberdeen, AB12 4YD

[enquiries@saltire-energy.com](mailto:enquiries@saltire-energy.com)

+44 (0)1224 872228

+44 (0)1224 897541

## **FAR EAST**

No.20 Tuas Ave 10, Singapore, 639144

[enquiries@saltire-energy.com](mailto:enquiries@saltire-energy.com)

+44 (0)1224 872228

+44 (0)1224 897541

## **MIDDLE EAST**

Musaffah, Abu Dhabi, 53161

[enquiries@saltire-energy.com](mailto:enquiries@saltire-energy.com)

+44 (0)1224 872228

+44 (0)1224 897541

## **NORWAY**

Hamrasletta 5, 4056 Tanager, Stavanger

[enquiries@saltire-energy.com](mailto:enquiries@saltire-energy.com)

+44 (0)1224 872228

+44 (0)1224 897541



[www.saltire-energy.com](http://www.saltire-energy.com)